



# NEVASTANE XS 80

## DESCRIPTION

**Extreme pressure, very low temperature, calcium sulfonate complex grease for food industry.**



**No MOAH (Mineral Oil Aromatic Hydrocarbons).**

\*The Nevastane range will not contribute to MOAH content in foods when used in accordance with FDA 21CFR178.3570 limitations.

## SPECIFICATIONS

- **NEVASTANE XS 80** is formulated in accordance with US FDA Regulation 21 CFR, 178.3570.
- **NEVASTANE XS 80** is **NSF H1** registered: No 147140 and ISO 21469 certified.
- ISO 6743-9 : L-XEFFF1/2
- DIN 51 502 : KP1/2R-55

## APPLICATIONS

- **NEVASTANE XS 80** is an extreme pressure grease dedicated to the lubrication in food industry under very severe conditions: low temperature, water, high load, dust.
- **NEVASTANE XS 80** is recommended for the lubrication of pelleting presses (KAHL, Promill Stolz, CPM, UMT, Van Aarsen...) in feed and sugar industries.

## ADVANTAGES

- **NEVASTANE XS 80** meets the most stringent industrial requirements.
- Extension of the equipment life while reducing contamination problems as required by the Hazard Analysis and Critical Control Point System (HACCP).
- Excellent mechanical and thermal stability (high dropping point).
- Remarkable load resistance thanks to its naturally high extreme pressure and anti-wear properties.
- Outstanding water and steam resistance and excellent food acids/alkalis resistance.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded at [ms-sds.totalenergies.com](http://ms-sds.totalenergies.com)

- No significant loss of consistency is observed even with high amounts of water entering the grease.
- Excellent anti-oxidation and anti-corrosion properties, also in the presence of salt water.

## RECOMMENDATIONS

- Store the product at temperatures between 0 and 35°C.
- Shelf life: 36 months from date of manufacture (unopened).
- Always avoid contamination of the grease by dust and/or dirt when applying

## TYPICAL CHARACTERISTICS

TYPICAL CHARACTERISTICS	METHODS	UNITS	NEVASTANE XS 80
Soap/thickener	-	-	Calcium Sulfonate Complex
Color	Visual	-	Light brown
Appearance	Visual	-	Smooth
NLGI grade	ASTM D 217	grade	1.5
Operating temperature range	-	°C	from -55 to 180
Penetration at 25 °C	ASTM D 217	0.1 mm	280-310
Four ball weld load	ASTM D 2596	kgf	>400
Anti-rust performance SKF-EMCOR	ISO 11007	rating	0 - 0
Dropping point	IP 396	°C	> 300
Flow pressure 1400 mbar	DIN 51805	°C (mbar)	<-55 (1385)
Kinematic viscosity of the base oil at 40 °C	ISO 3104	mm <sup>2</sup> /s	80


Above characteristics are mean values given as an information.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded at [ms-sds.totalenergies.com](http://ms-sds.totalenergies.com)

## TECHNICAL DATA SHEET

V.10/2024 NEVASTANE XS 80



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.  
A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded at [ms-sds.totalenergies.com](https://ms-sds.totalenergies.com)

**TotalEnergies Lubrifiants**  
SA 552 006 454 RCS Nanterre - France