



MULTIS MS 2

DESCRIPTION

Multi purpose extreme pressure lithium/calcium grease with molybdenum disulfide.

APPLICATIONS

MULTIS MS 2 is a true multi purpose grease, formulated for lubrication of various shock loaded or vibrating applications in transport, agriculture and off road equipment, operating in wet, dusty and/or dry conditions.

MULTIS MS 2 is suitable for boundary lubrication at high pressures and high temperatures. In case of accidental overheating, the presence of molybdenum disulfide will guarantee good lubrication, and avoid any jamming or sticking.

SPECIFICATIONS

ISO 6743-9: L-XBCEB 2

DIN 51 502: MPF2K -25

ADVANTAGES

MULTIS MS 2 forms a durable lubrication film, resulting in reduction of maintenance and down-time costs.

Miscible with most other conventional soap greases.

Excellent mechanical stability avoiding ejection or loss of consistency during operation.

Excellent adhesion to metal.

Good thermal stability, leading to high resistance to temperature variations.

MULTIS MS 2 does not contain lead, or other heavy metals considered harmful to human health and the environment.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

TotalEnergies Lubricants

SA 552 006 454 RCS Nanterre - France

RECOMMENDATIONS

Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

TYPICAL CHARACTERISTICS

TYPICAL CHARACTERISTICS	METHODS	UNITS	MULTIS MS 2
Soap/thickener		-	Lithium/ Calcium
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Grey
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 25 to 130
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265 - 295
Four ball weld load	ASTM D 2596	kg	400
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0 - 0
Dropping point	IP 396/DIN ISO 2176	°C	> 185
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm ² /s (cSt)	150

Above characteristics are mean values given as an information.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

TotalEnergies Lubricants

SA 552 006 454 RCS Nanterre - France