

Isovoltine P2

Inhibited mineral insulating fluid

APPLICATIONS

• **Isovoltine P2** oil is an inhibited mineral oil for transformers, switchgears, circuit breakers, welding set, and all high voltage electrical equipment.

ADVANTAGES

- Excellent resistivity, power factor and dielectric strength.
- Low viscosity for effective cooling
- Outstanding oxidation resistance providing long life.
- Very low pour point.
- No impurities such as dissolved gas, water or suspended solids.
- Does not contain DBDS.
- Does not contain PCB.

SPECIFICATIONS

- IEC 60296:2012 Inhibited
- BS 148 Class IA
- KS C 2301
- JIS C 2320 Class 1, Class IA, IIA
- Suitable for the equipment requiring ASTM D 3487 Type II fluid

APPROVALS



For additional information, contact your local Totalenergies Lubricants representative or visit our web site: <u>https://lubricants.totalenergies.com</u>

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded from https://sdstotalms.total.com

TECHNICAL DATA SHEET

17/07/2023 Ref. 0000000

TotalEnergies

TYPICAL CHARACTERISTICS

| Properties | Units | Standards | Isovoltine P2 |
|---|-------------------|-------------|----------------|
| Density at 20°C | gc/m ³ | ISO 3675 | 0.825 |
| Viscosity at 40°C | mm²/s | ISO 3104 | 7.70 |
| Flash point (Pensky Martens, Closed Cup) | °C | ISO 2719 | 145 |
| Pour point | °C | ISO 3016 | -45 |
| Acidity | mg KOH/g | IEC 62021-1 | < 0.01 |
| Water content | ppm | IEC 60814 | 17 |
| Antioxidant additives | %wt | IEC 60666 | < 0.08 |
| Corrosive sulfur | - | DIN 51353 | Non corrosive |
| Breakdown voltage | kV | IEC 60156 | > 30 |
| DDF at 90°C | % | IEC 60247 | < 0.001 |
| Oxydation stability, 332 h - Sludge - Total Acidity | %wt mg KOH/g | IEC 611256C | < 0.01 0.12 |



For additional information, contact your local Totalenergies Lubricants representative or visit our web site: https://lubricants.totalenergies.com This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded from https://sdstotalms.total.com